

Wilderness Design Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Average Weight / Unit (kg)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Cold Water Absorption	Initial Rate Of Absorption	Efactor	Durability Class	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv	Basix	Frl
Wilderness Design	Blue Gum			NSW	230	110	76	DW1	2.7	48.5	520	>15		0.5 to 3		Exposure Grade	Slight	Slight	0.86	7.9	Dark	90/90/90
Wilderness Design	Silver Birch NSW			NSW	230	110	76	DW1	2.7	48.5	400	>15		0.5 to 3		Exposure Grade	Slight	Slight	0.669	25.31	Medium	90/90/90
Wilderness Design	Flooded Gum			NSW	230	110	76	DW2		48.5	520	>10		0.5-2.0		Exposure Grade	Slight	Slight	0.7	14.3		90/90/90
Wilderness Design	Grey Gum			NSW	230	110	76	DW1		48.5	400	>10	10	0.5 to 3	1.2	Exposure Grade	Slight	Slight	0.71	15.6	Dark	90/90/90
Wilderness Design	Blackbutt NSW			NSW	230	110	76	DW1	2.7	48.5	400	>10		0.5 to 3		Exposure Grade	Slight	Slight	0.848	6	Dark	90/90/90
Wilderness Design	Blackbutt			NSW	230	110	76	DW1	2.7	48.5	520	>10		0.1-1.0		Exposure Grade	Slight	Slight	0.85	6.6	Dark	90/90/90
Wilderness Design	Silver Birch			NSW	230	110	76	DW1		48.5	520	>10		0.1-1.0		Exposure Grade	Slight	Slight	0.73	18.9	Medium	90/90/90

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.